



Product Name: Red Stone Bitumen 60/70

Production Date: June 2025

Manufacturer: Red Stone International

Location: East Ahmadi Industrial Area, Block 6, Plot 70, Kuwait

Bitumen 60/70

Bitumen 60/70	Specification	Test method
Specific gravity @ 25/25 cg	1.01/1.06	D-70
Penetration @ 25 c	60/70	D-5
Softening point c	48/52	D-36
Ductility @25 c	100 min	D-113
Loss on heating(wt) %	0.2 Max	D-6
Drop in penetration after heating %	20 Max	D-6 D-5
Flash point c	250 min	D-92
Solubility is CS2(wt) %	99.5 Max	D-4
Spot test	negative	A.A.S.H.O.T102